



Product Technical Information Sheet Wienerberger Code 24311350

Hartlebury 2 **Production Plant**

Extruded/Wirecut Manufacture

Perforated Configuration

Red Multi Colour

Rolled Appearance

215 x 102.5 x 65 Work Size (mm)

Pack Quantity 430 No.

Individual Dry Brick Weight (kg) 1.7



Technical Properties to BS EN 771-1

Size Tolerance (Mean/Range)	T2/R1
Gross Dry Density (kg/m³/Tolerance)	1150 (D1)
Compressive Strength (N/mm²)	≥30
Thermal Conductivity (W/(m·K)) $\lambda_{10,dry,unit}$ value (EN 1745 tabulated: S1)	P=90% 0.60
Durability Designation	F2
Water Absorption (%)	≤15
Initial Rate of Water Absorption (kg/(m²·min))	Min. 0.3 Max. 2.0
Active Soluble Salts	S2
Reaction to Fire	Class A1

Issue Date: 09/05/2023

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.





1000+ products to choose from



Expert help and advice



t 0161 491 8200

Comprehensive Design Services



Technical Support